

# **DENSOPOL 80 & 80HT TAPE**

## **Heavy Duty PVC/Bitumen Fabric-Reinforced Tape**

### **Description**

Densopol 80 & 80 HT are extremely tough cold-applied laminate tapes. The combination of PVC backing and fabric reinforced polymer bitumen adhesive makes it extremely resistant to damage by sharp objects e.g. poor backfill.

### **Uses**

For the corrosion protection of buried or immersed pipes and fittings. The tapes can be applied by hand to weld joints, bends, bare pipe lengths and pipe fittings.

### **Features**

- Cold applied
- Good conformability
- Good impact resistance
- Excellent adhesion to pipe and self
- Excellent resistance to cathodic disbonding
- Compatible with common pipe coatings
- Suitable for application by hand or machine on medium or large diameter pipes

### **Application**

Prepare steel to St2 (power brushed)/AS 1627 P.2 (minimum). Apply thin film of Denso Primer D to all surfaces to be protected and allow to tack dry. Peel back interleaving and apply adhesive side of the tape to the primed surface and press down. Apply the tape spirally with enough tension to make it conform. Remove interleaving as wrapping proceeds. Overlap each turn by 55% to achieve double thickness.

Irregular surfaces such as valves, flanges, etc. may require the use of Denso Bitumen Mastic, Denso Mastic or Denso Profiling Mastic. Refer to the product sheets for specific product for information on application.



# Densopol 80 & 80HT Tape

## Property Specifications

<b>PROPERTIES</b>	<b>DENSOPOL 80 VALUE</b>	<b>DENSOPOL 80HT VALUE</b>
Thickness (ASTM D1000)		
PVC Carrier	0.50 mm	-
Reinforcement & Adhesive	1.50 mm	-
Total	2.0 mm	1.85 ± 0.25 mm
Weight	2.4 kg/m <sup>2</sup>	2.8 ± 0.20 kg/m <sup>2</sup>
Breaking Strength @ 23°C (ASTM 1000)	9 N/mm	8 N/mm min
Breaking Strength @ 40°C (ASTM 1000)	-	5 N/mm
Tear Strength (ASTM 1004)	36 N	70 N min
Elongation @ Break (ASTM D1000)	22%	22%
Adhesion Peel Strength (ASTM D1000, 24 h)		
To Primed Steel @ 23°C	2.2 N/mm	3.0 - 5.0 N/mm
To Primed Steel @ 50°C	-	0.4 N/mm
To Self @ 23°C	2.2 N/mm	2.0 - 4.0 N/mm
To Self @ 50°C	-	0.3 N/mm
Insulation Resistance	10 <sup>6</sup> megohms	10 <sup>6</sup> megohms
Impact Strength @ 23°C (Double layer, ASTM G14)	9 Nm	8 Nm min
Impact Strength @ 40°C (Double layer, ASTM G14)	-	5 Nm
Indentation Resistance (Double layer, DIN 30672 Pt. 1 Class C)		
Residual Thickness @ 23°C	-	0.8 mm
Residual Thickness @ 40°C	-	0.5 mm
Continuity @ 15 kV After Indentation	-	Pass at 23°C & 40°C
Dielectric Strength	20 kV/layer	20 kV/layer
Resistance to Cathodic Disbondment (ASTM G8, Method A, 23°C. 30 day)	Excellent	20 mm radius max
Water Vapour Transmission (Double Layer, ASTM E96 32°C/50% RH)	-	0.55 g/m <sup>2</sup> /day
Temperature Range		
For Application	8°C to 45°C	18°C to 50°C
For Service	-20°C to 60°C	-10°C to 60°C
Recommended Holiday Test Voltage		
Single Layer	10 kV	10 kV
Double Layer	15 kV	15 kV
Recommended Primer	Denso Primer D	Denso Primer D
Colour (Backing)	Black	Black

## Quantity Estimates

Tape Width	Tape Length	Rolls/Case	Coverage with 55% Overlap
in.	ft.	ea.	ea.
2" (50 mm)	33' (10 m)	24	59 ft <sup>2</sup> (5.5 m <sup>2</sup> )/case
4" (100 mm)	33' (10 m)	12	59 ft <sup>2</sup> (5.5 m <sup>2</sup> )/case
6" (150 mm)	33' (10 m)	8	59 ft <sup>2</sup> (5.5 m <sup>2</sup> )/case



**DENSO (AUSTRALIA) PTY LTD**

77 - 95 National Boulevard  
Campbellfield, VIC 3061  
Tel: +61 3 9356 7600  
Fax: +61 3 9356 7699

[www.densoaustralia.com.au](http://www.densoaustralia.com.au)

**A Member of the Winn & Coales International**

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.