

DENSO GLASS OUTERWRAP

Protective Fiberglass Outerwrap

Description

Denso Glass Outerwrap is a fiberglass cloth impregnated with a water activated resin that is used as a protective outer wrap over Denso Tape. It is a protective coating which offers exceptional mechanical and impact strength for underwater, underground and above ground pipe.

Uses

- Repairs and reinforcement for water, steam, sewage, air and fuel pipes
- Structural repairs and the sealing of joints and ducts
- Corrosion protection, sealing, waterproofing (including immersed substrates)
- Electrical insulation and dielectric protection

Features

- Highly resistant to chemical attack
- Resists cold and hot temperatures
- Easy to apply, no mixing or messy clean up
- Resistant to water, acids, salts, or soil organics
- Can be applied underwater or to wet surfaces
- Minimal surface preparation required
- Quick, long term protective coating, ready for immediate service
- Compatible with many substrates including steel, copper, PVC, fiberglass, clay, concrete, rubber, and more
- Contains no solvents
- Paintable
- Pressure once cured: 2.07 MPa maximum

Application

Prepare surfaces by removing all loose scale, rust or other foreign matter in accordance to SSPC SP2 "Hand Tool Cleaning" or SP3 "Power Tool Cleaning". High pressure water wash of 20 - 48 MPa is also suitable. Spirally wrap a layer of Denso Tape at a 55% overlap. While wrapping, press air pockets out and smooth all lap seams.

Using rubber gloves, remove the Denso Glass Outerwrap from the hermetically sealed foil pouch and soak in temperate water (salt or fresh) for 20 to 30 seconds. Remove and begin wrapping tightly, overlapping at a recommended 55%.

Irregular surfaces such as valves, flanges, etc. may require the use of Denso Mastic or Denso Profiling Mastic. Refer to the individual product data sheets for information on specific products and application.



Denso Glass Outerwrap

Property Specifications

PROPERTIES	VALUE
Colour	White
Flexural Strength (ASTM D790)	180 MPa
Tensile Strength (ASTM D638)	248 MPa
Lap Shear Strength (ASTM D5379)	6.2 MPa
Dielectric Strength (ASTM D149)	16 kV
Impact Résistance (ASTM G14/G62)	167 J
Chemical Resistance (ASTM D543, 2 Months at 23°C)	
Sulfuric Acid, 10%	<i>No Change</i>
Sulfuric Acid, 50%	<i>No Change</i>
Hydrochloric Acid, 10%	<i>No Change</i>
Hydrochloric Acid, 50%	<i>No Change</i>
Sodium Hydroxide Solution, 20%	<i>No Change</i>
Gasoline	<i>No Change</i>
Toluene	<i>No Change</i>
Xylene	<i>No Change</i>
Mineral Spirits	<i>No Change</i>
Nitric Acid, 50%	<i>Blistering</i>
Distilled Water	<i>No Change</i>
Product sizes	100 mm x 9.1 m 200 mm x 12.2 m
Application Temperature	0°C to 65°C
Service Temperature	-45°C to 121°C

Average Temperature	Approx. Working Time	Return to Service Time
35°C	3 min	23 min
21°C	8 min	28 min
16°C	10 min	85 min (1 h. 25 min)
10°C	14 min	162 min (2 h. 42 min)
6°C	17 min	182 min (3 h. 2 min)
2°C	20 min	381 min (6 h. 21 min)

SHELF-LIFE: 24 months

STORAGE: In original cartons and in a cool, dry place away from direct sunlight.



DENSO (AUSTRALIA) PTY LTD

77 - 95 National Boulevard
Campbellfield, VIC 3061
Tel: +61 3 9356 7600
Fax: +61 3 9356 7699

www.densoaustralia.com.au

A Member of the Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.