

**Archco-Rigidon 606E** is normally applied to suitably prepared and primed steel or concrete substrates.

The silica filled base coat is applied by trowel to a nominal thickness of 1.5mm and is immediately followed by a laminate consisting of a chemically resistant resin combined with two layers of 450g/m<sup>2</sup> chopped strand mat. A surface tissue is applied over the laminate and is followed, after curing, with an epoxy top coat.

### Preparation and Application of the Base Coat

Thoroughly mix the unactivated base resin using a mechanical whip. The material should then be activated. Ensure the two components are fully mixed using a mechanical whip.

Add the FS1 Filler to the activated base coat resin in a 2:1 filler/resin ratio. Fully blend in the filler powder with a mechanical whip. Never mix more material than can be applied within the stated pot life.

The filled base coat should be trowelled onto the substrate with a plastering trowel in strips approx. 1.2 metres wide.

### Preparation and Application of the Laminate

Thoroughly mix the unactivated resin using a mechanical whip. The material should then be activated. Ensure the two components are fully mixed using a mechanical whip prior to application. Cut 2 strips of 450g/m<sup>2</sup> CSM and 1 strip of Surface Tissue of sufficient size to overlay onto the base coat; the base coat should extend beyond the edges of the CSM and tissue by approx. 50mm.

Apply the first layer of CSM directly to the base coat while it is still wet and roll with a metal ribbed roller – this will ensure a good bond between the base coat and laminate. Wet out the CSM using the series 606E resin and roll out to expel any air entrapment. The second layer of CSM is applied in a similar manner, as is the subsequent layer of Surface Tissue. When consecutive areas are coated the laminate must overlap the adjacent newly applied lining, having an overlap of 50mm at each joint.

### Topcoat (Optional)

Use Denso ST Epoxy.

System 606E	
Application Method	Trowel and hand lay up
Activator	Activator Part B
Volume Solids	100%
Specific Gravity	1.2
Dry Film Thickness	Approx. 3mm
Practical Spreading Rate	Refer to relevant Data Sheet Doc. Ref. 21A/606E
Overcoating Times Base and Laminate Topcoat and Laminate	Wet on wet system Min 6 hrs-Max 7 days
Tool Cleaning Solvent	Epoxy Thinners
Max Humidity during Application	90% Rh
Min Substrate Temperature	10°C
Min Dewpoint/Substrate Differential	Dewpoint +3°C
Preferred Equipment	Trowel, Brush and Roller
Pot Life	40 mins-60 mins
Dilution	N/A
Shelf Life	6 months
Storage Temperature Limits	10°C - 20°C
Flash Point	31°C
Ventilation	Do not use in confined spaces without adequate ventilation or breathing equipment
Lighting – Heating in an Enclosed Environment	Use only BASEFA Zone 1 Eex d IIA or better

### Notes

Pay particular attention to the stated pot life of the material (see material package labelling). Clean down tools and equipment with **Epoxy Thinners** within this specified time. Great care must be taken to avoid contaminating the coating material with **Epoxy Thinners** as this can have adverse effects on the cure of the material.