



Approved Quality
Management System
AS/NZS ISO 9001:2008
Lloyds Register-Certificate
No. MEL 0927759

Technical Data Sheet

ULTRAFLEX 1500 TAPE

Description:	A bitumen based adhesive corrosion protection tape. An integral component of the Denso Ultraflex System.
Composition:	A heavy duty PVC backing coated with a bitumen based adhesive compound. Includes a release liner (interleaving) which is removed prior to use, for ease of application and handling.
Characteristics:	<ul style="list-style-type: none"> • sticks and bonds rapidly and permanently to clean dry primed surfaces • fast and simple application by hand or machine • flexible, long lasting, self sealing to minor substrate blemishes • secure lap sealing on edges and overlaps • specially designed high impact PVC backing ensuring rugged durability and a high degree of conformability and controlled elasticity • stable in composition over a wide temperature range • non hardening or cracking • accommodates vibration and movement of substrate • highly resistant to mineral acids, alkalis and salts • will adhere and remain attached to petrolatum based tapes • highly resistant to cathodic disbondment • protruding interleaving prevents edge of roll dirt "pick-up" during site handling, minimising contamination risk and assuring coating integrity • contains no volatile components
Uses:	<ul style="list-style-type: none"> • designed for the corrosion protection of pipelines, joints, culverts, welds, bends and fittings • used in conjunction with Denso Primer D and Bitumen Mastic Strip to contour and protect irregular surfaces and shapes
Surface Preparation:	Prepare steel to St2 (power brushed) / AS1627 P.2 (minimum) Edges should be chamfered to remove step down. Approximately a 100mm band of any pre-existing factory coatings should be abraded and solvent (toluene) degreased either side of a joint.
Application:	<p>Primer Denso Primer D should be applied to the prepared substrate at a rate of 9 - 11 m²/litre and allowed to tack dry (10 to 20 minutes), prior to the use of Bitumen Mastic Strip or Ultraflex 1500 Tape.</p> <p>Profiling Denso Bitumen Mastic Strip should be applied to contour weld beads and step downs on shop coatings so that subsequent tape wrapping can conform smoothly to the substrate being protected. The mastic can be cut into smaller strips and moulded into crevices and cavities.</p> <p>Wrapping Apply Ultraflex 1500 Tape with compound side to substrate, creating a 55% overlap of tape to effectively provide a double layer. Smooth down and mould tape by hand, especially at all overlapped edges.</p>
Recommended Temperatures:	<p>Application: + 15 to + 50 °C</p> <p>Service: - 20 to + 65 °C</p> <p>Peak: + 70 °C</p>
Storage:	Store in a cool, dry area away from direct heat and sunlight.



Approved Quality
Management System
AS/NZS ISO 9001:2008
Lloyds Register-Certificate
No. MEL 0927759

Technical Data Sheet
ULTRAFLEX 1500 TAPE

Product code/ Available Sizes:	B708050: 50 mm x 10 m B708100: 100 mm x 10 m B708150: 150 mm x 10 m Other sizes available on request.
---	--

Physical Properties:	Test	Method	Units	Value
	Total Thickness	ASTM D1000	mm	1.50 ± 0.13
	Total Weight	ASTM D751	kg/m ²	1.75 ± 0.13
	Breaking Strength	ASTM D1000	N/mm	8.0
	Elongation at Break	ASTM D1000	%	250
	Adhesion - to steel - to self	ASTM D1000	N/mm	≥ 3.0 ≥ 3.0
	Tear Resistance	ASTM D1004	N	25
	Impact Strength - round tup - chisel tup	ASTM G14 BGC/PS/CW2	Joule	7.0 3.5
	Dielectric Strength	ASTM D149	kV	≥ 30
	Insulation Resistance	BS 2782 (204A)	Ω	> 10 ¹²
	Cathodic Disbondment	ASTM G8 (30 days)	mm ² Group	< 160 A