



Approved Quality  
Management System  
AS/NZS ISO 9001:2008  
Lloyds Register-Certificate  
No. MEL 0927759

## Technical Data Sheet

# SINGLE-PACK ELASTOMERIC MEMBRANE (Brush Grade)

<b>Description:</b>	Denso Single-Pack Elastomeric Membrane cures to form a tough, flexible, waterproofing and sealing membrane
<b>Composition:</b>	A single component, moisture curing, polyurethane based membrane
<b>Characteristics:</b>	<ul style="list-style-type: none"> <li>• Room temperature processing and curing</li> <li>• High resistance to puncture, fouling and stagnant water</li> <li>• Excellent crack bridging capability</li> <li>• Quick tack-free surface</li> <li>• High UV resistance</li> <li>• Monolithic membrane—no seams</li> <li>• Elastomeric behaviour: remains flexible at low temperatures</li> <li>• High elongation, class III membrane according to AS/NZ 4858</li> <li>• No reinforcement required</li> <li>• Low VOC, complies with Green Star requirements</li> <li>• Low odour</li> <li>• Recommended substrate moisture: 5%</li> <li>• Recommended relative humidity: 20-90%</li> </ul>
<b>Uses:</b>	<p>Ideal for sealing petrolatum tapes as in the Denso Steelcoat 100 System. Ideal for sealing fabric backed bitumen tapes as in the Denso Steelcoat 400/500 System.</p> <p>Waterproofing membrane compatible with metal, concrete, compressed fiber-cement sheets or timber surfaces.</p>
<b>Surface Preparation:</b>	<p>Surfaces must be sound, dry, clean and free from loose materials and oil. Protrusions which may penetrate the membrane must be removed. Must not be applied on wet or damp surfaces.</p> <p>A layer of diluted Single-Pack Elastomeric Membrane (diluted to 10% with xylene) can be used as a primer for dry/contaminant free concrete. The use of an epoxy primer is recommended in case of high porosity or wet concrete (humidity &gt;5%). Compatibility of the primer with the membrane must be checked prior to application. Dilution with any solvent other than xylene is not permitted.</p>
<b>Application:</b>	<p><u>Application:</u> Apply the initial coating of Denso Single-Pack Elastomeric Membrane using brush or roller to the desired thickness.</p> <ul style="list-style-type: none"> <li>• Two coats of 900 g/m<sup>2</sup> (approx. 675 µm on a film thickness gauge) are required to achieve dry film thickness of 1 mm.</li> <li>• Two coats of 1050 g/m<sup>2</sup> (approx. 790 µm on a film thickness gauge) are required to achieve a dry film thickness of 1.2 mm.</li> </ul> <p>For vertical application, a coverage rate of 900 g/m<sup>2</sup> is required to avoid sagging.</p> <p><u>Recoating:</u> Denso Single-pack Elastomeric recoated with a second layer of the coating after one night and within two days. In case of rain or if the recoating window is exceeded, substrate should be ground.</p> <p>Equipment can be cleaned with xylene, mineral turps, or methylated spirits</p>



Approved Quality  
Management System  
AS/NZS ISO 9001:2008  
Lloyds Register-Certificate  
No. MEL 0927759

## Technical Data Sheet

### **SINGLE-PACK ELASTOMERIC MEMBRANE (Brush Grade)**

#### **CORROSION PREVENTION**

<b>Recommended Temperatures:</b>	Substrate: + 5 to + 35°C Service: - 20 to + 80°C			
<b>Shelf Life: Storage:</b>	≥ 9 months when stored in original containers. Storage temperatures: 5°C to 35°C Moisture sensitive product. Store in a cool, dry area away from heat and direct sunlight in tightly sealed containers. Keep away from oxidising agents.			
<b>Product Code/ Available Sizes:</b>	M310003: 4 L			
<b>Physical Properties:</b>	<b>Test</b>	<b>Test Method</b>	<b>Units</b>	<b>Value</b>
	Colour	-	-	Grey
	Curing time	-	Hours	16 (overnight)
	Density (liquid)	ASTM D1475-13	g/cm <sup>3</sup>	1.30-1.35
	Density (cured)	AS 1683.4	g/cm <sup>3</sup>	1.40 - 1.45
	Viscosity @ 30 rpm	Brookfield	cP	12,000- 18,000
	Hardness	AS 1683.15.2	Shore A	70
	Angle tear strength	AS 1683.12	Kg/cm	20
	Tensile Strength	AS 1683.11	MPa	6
	Elongation	AS 1683.11	%	300
	Non-volatile matter	ASTM D2369-10	%	81
	VOC Content	ASTM D2369-10	g/L	250
<b>Limitations:</b>	If surface skinning occurs, carefully remove skin. Do not blend skin back into liquid.			
<b>Precautions:</b>	Safety goggles and rubber gloves are recommended. Avoid skin and eye contact. Overexposure may cause sensitisation. Do not apply by spray. Follow all precautions found in Safety Data Sheets, product labels and technical literature.			