

DENSOPOL 80™ & 80HT™ TAPE

Heavy Duty PVC/Bitumen Fabric-Reinforced Tape

Description

Densopol 80 & 80 HT are extremely tough cold-applied laminate tapes. The combination of PVC backing and fabric reinforced polymer bitumen adhesive makes it extremely resistant to damage by sharp objects e.g. poor backfill.

Uses

For the corrosion protection of buried or immersed pipes and fittings. The tapes can be applied by hand to weld joints, bends, bare pipe lengths and pipe fittings.

Features

- Cold applied
- Good conformability
- Good impact resistance
- Excellent adhesion to pipe and self
- Excellent resistance to cathodic disbonding
- Compatible with common pipe coatings
- Suitable for application by hand or machine on medium or large diameter pipes

Application

Prepare steel to St2 (power brushed)/AS 1627 P.2 (minimum). Apply thin film of Denso Primer D™ to all surfaces to be protected and allow to tack dry. Peel back interleaving and apply adhesive side of the tape to the primed surface and press down. Apply the tape spirally with enough tension to make it conform. Remove interleaving as wrapping proceeds. Overlap each turn by 55% to achieve double thickness. If holiday testing is required, the recommended voltages are 10 kV for single layer or 15 kV for double layer.

Irregular surfaces such as valves, flanges, etc. may require the use of Denso™ Bitumen Mastic, Denso™ Mastic or Denso™ Profiling Mastic. Refer to the product sheets for specific product for information on application.



Densopol 80™ & 80HT™ Tape

Property Specifications

PROPERTIES	DENSOPOL 80	DENSOPOL 80HT
	VALUE	VALUE
Colour	Black	Black
Thickness (ASTM D1000)		
PVC Carrier	0.50 mm	-
Reinforcement & Adhesive	1.50 mm	-
Total	2.0 mm	1.85 ± 0.25 mm
Weight	-	2.28 ± 0.20 kg/m ²
Breaking Strength @ 23°C (ASTM 1000)	10 N/mm	10 N/mm
Breaking Strength @ 40°C (ASTM 1000)	-	5 N/mm
Tear Strength @ 23°C (ASTM 1000)	36 N	75 N min
Modulus @ 10% Extension		
@ 23°C	-	8 N/mm
@ 40°C	-	4 N/mm
Elongation @ Break (ASTM D1000)	22%	22%
Adhesion Peel Strength (ASTM D1000, 24 h)		
To Primed Steel @ 23°C	2.2 N/mm	3.0 - 5.0 N/mm
To Primed Steel @ 40°C	-	0.4 N/mm
To Self @ 23°C	2.2 N/mm	2.0 - 4.0 N/mm
To Self @ 40°C	-	0.3 N/mm
Insulation Resistance	10 ⁶ megohms	10 ⁶ megohms
Impact Strength @ 23°C (Double layer, ASTM G14)	9 Nm	10 ± 2 Nm
Impact Strength @ 40°C (Double layer, ASTM G14)	-	5 Nm
Indentation Resistance (Double layer, DIN 30672 Pt. 1 Class C)		
Residual Thickness @ 23°C	-	0.8 mm
Residual Thickness @ 40°C	-	0.5 mm
Continuity @ 15 kV After Indentation	-	Pass at 23°C & 40°C
Breakdown Voltage (ASTM D1000)		
Single Layer @ 23°C	20 kV	20 kV
Double Layer @ 23°C	-	40 kV
Resistance to Cathodic Disbondment (ASTM G8, Method A, 23°C, 30 day)	Excellent	20 mm radius max
Water Vapour Transmission (Double Layer, ASTM E96 32°C/50% RH)	-	0.55 g/m ² /day
Temperature Range		
For Application	8°C to 45°C	18°C to 50°C
For Service	-20°C to 60°C	-10°C to 60°C
Peak	-	75°C

Quantity Estimates

Tape Width	Tape Length	Rolls/Case	Coverage with 55% Overlap
in.	ft.	ea.	ea.
2" (50 mm)	33' (10 m)	24	59 ft ² (5.5 m ²)/case
4" (100 mm)	33' (10 m)	12	59 ft ² (5.5 m ²)/case
6" (150 mm)	33' (10 m)	8	59 ft ² (5.5 m ²)/case



DENSO (AUSTRALIA) PTY LTD

77 - 95 National Boulevard
Campbellfield, VIC 3061
Tel: +61 3 9356 7600
Fax: +61 3 9356 7699

www.densoaustralia.com.au

A Member of the Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.