## PRODUCT DATA SHEET

# DENSOPOL 60 & 60HT TAPE Heavy Duty PVC/Bitumen Fabric-Reinforced Tape

# Description Densopol 60 & 60 HT is a cold applied, synthetic fabric reinforcement coated with rubber bitumen adhesive and backed with a PVC film. Uses For the corrosion protection of buried or immersed pipes and fittings. Used for external joint sealing to prevent backfill infiltration in concrete pipes, culverts and crown units. The tapes can be applied by hand to weld joints, bends, bare pipe lengths and pipe fittings. Features • Applied to marginally prepared surfaces (SSPC SP 2-3) • Cold applied • Good comformability • Good impact resistance • Excellent adhesion to pipe and self

- Excellent adhesion to pipe and sell
- Excellent resistance to cathodic disbonding
- Compatible with common pipe coatings

### Application

Prepare steel to St2 (power brushed)/AS 1627 P.2 (minimum). Surface must be clean, dry and free of grease. Apply thin film of Denso Primer D to all surfaces to be protected and allow to dry. Peel back interleaving and apply adhesive side of the tape to the primed surface and press down. Apply the tape spirally with enough tension to make it conform. Remove interleaving as wrapping proceeds. Overlap each turn by 55% to achieve double thickness.

Irregular surfaces such as valves, flanges, etc. may require the use of Denso Bitumen Mastic, Denso Mastic or Denso Profiling Mastic. Refer to the product sheets for these specific products for information on application and selection.



# Densopol 60 & 60HT Tape

### **Property Specifications**

	DENSOPOL 60	Densopol 60HT Value
PROPERTIES	VALUE	
Thickness (ASTM D1000)		
Backing	0.085 mm	0.085 mm
Adhesive	1.515 mm	1.515 mm
Total	1.60 mm	1.60 mm
Weight	1.8 kg/m²	1.8 kg/m²
Breaking Strength (ASTM 1000)	8 N/mm	8 N/mm
Tear Strength (ASTM 1004)	20 N	20 N
Elongation @ Break	22%	22%
Adhesion Peel Strength (ASTM D1000)		
To Primed Steel	2.5 N/mm	3.0 N/mm
To Self	2.5 N/mm	2.5 N/mm
Impact Strength (ASTM G-14)	4 N/mm	5 N/mm
Dielectric Strength	20 kV	20 kV
Resistance to Cathodic Disbondment		
(ASTM G-8 30 Days Group B)	350 mm <sup>2</sup> avg. 350 mm <sup>2</sup> avg.	
Temperature Range		
For Application	5°C to 45°C	15°C to 50°C
For Service	60°C	75°C
Recommended Holiday Test Voltage		
Single Layer	10 kV	10 kV
Double Layer	15 kV	15 kV
Roll Widths	50, 100, 150 mm	50, 100, 150 mm
Roll Length	10 m	10 m
Recommended Primer	Denso Primer D	Denso Primer D
Color (Backing)	Black	Black

### **Quantity Estimates**

Tape Width	Tape Length	Rolls/ Case	Coverage with 55% Overlap
in.	ft.	ea.	ea.
2" (50 mm)	33' (10 m)	24	59 ft <sup>2</sup> (5.5 m <sup>2</sup> /case)
4" (100 mm)	33' (10 m)	12	59 ft <sup>2</sup> (5.5 m <sup>2</sup> /case)
6" (150 mm)	33' (10 m)	8	59 ft <sup>2</sup> (5.5 m <sup>2</sup> /case)



77 - 95 National Boulevard Campbellfield, VIC 3061 Tel: +61 3 9356 7600 Fax: +61 3 9356 7699

www.densoaustralia.com.au

A Member of the Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.