

DENSO MP PRIMER

Petrolatum Tape Primer

Description

Denso MP Primer is a soft brown petrolatum primer containing moisture displacing, corrosion inhibiting compounds for application by stiff brush or gloved hand at normal ambient temperature. It does not dry, harden or crack.

Uses

Primarily used as a primer prior to the application of Denso petrolatum tapes. Denso MP Primer will penetrate existing rust, displace moisture, pacify the surface and aid the adhesion of petrolatum tapes and mastics. It is also used as a temporary coating for exposed metal.

Features

- Minimal surface preparation (SSPC SP 2-3)
- Can be applied in any climate
- Contains no VOCs
- Accommodates vibration and movement of substrate
- Highly resistant to mineral acids, alkali and salts
- Can be applied by inexperienced personnel
- No shut downs necessary

Application

Prepare surfaces by removing all loose scale, rust or other foreign matter in accordance to SSPC SP2 "Hand Tool Cleaning" or SP3 "Power Tool Cleaning". High pressure water wash of 3,000 - 7,000 psi (20.68 - 48.48 MPa) is also suitable. Firmly adherent rust and scale need not be removed. Apply a thin uniform coat of Denso MP Primer to entire surface with gloved hand, brush or rag. Estimated coverage rate is 2 - 5 m²/kg.



Denso MP Primer

PROPERTY SPECIFICATIONS

PROPERTIES	VALUE
Solids Content	>98%
Specific Gravity	1.08
Specific Volume	925 cc/kg
Uncut Cone Penetration (ASTM D937)	160 ± 20 dmm
Flash Point	>180°C
Application Temperature	-5°C to 45°C
Service Temperature	-20°C to 50°C
Peak Intermittent Temperature	55°C
Coverage Rate	2 - 5 m ² /kg

PACKAGING:

2.5 kg (4/Carton)

15 kg (1/Carton)

STORAGE:

In cool, dry conditions and away from heat and direct sunlight.



DENSO (AUSTRALIA) PTY LTD

77-95 National Boulevard

Campbellfield, VIC 3061

Tel: +61 3 9356 7600

Fax: +61 3 9356 7699

www.densoaustralia.com.au

A Member of Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.