

## DENSO MARINE PILING TAPE™

### Marine Petrolatum Tape with HDPE Backing

#### Description

Denso Marine Piling Tape is composed of a non-woven synthetic fabric carrier, fully impregnated with a compound based on petrolatum containing inert fillers and water displacing agents. It is backed with a thin high-density polyethylene film.

#### Uses

Denso Marine Piling Tape is designed to be used without primer to protect dry, wet or submerged surfaces. The tape provides long term protection to pipes, pilings, risers, flanges, valves and related surfaces. When applied in the splash zone, the tape shall be protected with a specified SeaShield™ outercover.

#### Features

- Meets NACE RP0375-2006
- Applied to marginally prepared surfaces (SSPC SP 2-3)
- Conforms to irregular shapes and profiles
- Can be applied to cold, wet surfaces
- Not effected by water, acid, salts or soil organics
- Encapsulation of lead paint
- Contains no solvents
- Easy application from arctic to tropical temperatures
- Ready for immediate service after application
- Does not require a primer
- Over a sixty-five year history of proven applications

#### Application

Prepare surfaces by removing all loose scale, rust or other foreign matter in accordance to SSPC SP2 "Hand Tool Cleaning" or SP3 "Power Tool Cleaning". High pressure water wash of 3,000 - 7,000 psi (21 - 48 MPa) is also suitable. Spirally wrap the tape with a 55% overlap. While wrapping, press air pockets out and smooth all lap seams. When applied in the splash zone, the tape shall be protected with a specified SeaShield outercover.

Irregular surfaces such as valves, flanges, etc. may require the use of Denso™ Mastic or Denso Profiling Mastic™. Refer to the product data sheets for these specific products for information on application and selection.



# Denso Marine Piling Tape™

## PROPERTY SPECIFICATIONS

PROPERTIES	VALUE
Thickness (ASTM D1000)	1.3 mm avg.
Weight	1.62 kg/m <sup>2</sup> avg.
Breaking Strength (ASTM 1000)	200 N/50 mm min.
Elongation @ Break	10% avg.
Breakdown Voltage (55% overlap)	16 kV min.
Resistance to Cathodic Disbonding (ASTM G-8 - 30 days)	180 mm <sup>2</sup> avg.
Resistance to Acids, Alkalies and Salts	Excellent
Maximum Service Temperature	60°C

## Quantity Estimates

Tape Width	Rolls*/ Case	Coverage with 55% Overlap
mm.	ea.	ea.
150 mm	8	58 ft <sup>2</sup> ( 5.4m <sup>2</sup> )/case
200 mm	8	78 ft <sup>2</sup> (7.2 m <sup>2</sup> )/case
300 mm	4	58 ft <sup>2</sup> (5.4m <sup>2</sup> )/case

\*All rolls are 33 feet (10 meters) in length.



**DENSO (AUSTRALIA) PTY LTD**

77 - 95 National Boulevard  
Campbellfield, VIC 3061

Tel: +61 3 9356 7600

Fax: +61 3 9356 7699

[www.densoaustralia.com.au](http://www.densoaustralia.com.au)

**A Member of the Winn & Coales International**

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.