



# Protal™ 7900HT

## Brush Application Specifications

### 1.0 Scope

- 1.1 This specification covers the external surface preparation and coating of pipeline applications such as weld joints, special pipe sections, fittings and fabrication.

### 2.0 Material and Storage

- 2.1 Material shall be Denso Protal™ 7900HT as supplied by Denso (Australia) Pty Ltd.
- 2.2 Material shall meet the physical properties of the attached product data sheet.
- 2.3 Storage: Material shall be stored in a warm, dry place between 40°F to 100°F. (4.4°C to 37.7°C) Care shall be taken to insure the material is stored up right (arrows on boxes facing up). *Note: If the material is kept cold, it will become very viscous.*

### 3.0 Equipment

- 3.1 For mixing, use strong wooden stir sticks or power drills with appropriate mixing paddle.
- 3.2 For application, use 4" (100 mm) wide brushes, Denso applicator pads or Protal™ 9" (225 mm) roller.
- 3.3 Wet film thickness gauges.

### 4.0 Surface Preparation

- 4.1 Material for abrasive cleaning shall be the appropriate blend of grit to produce an angular surface profile of 2.5 - 5 mils (0.063 - 0.125 mm).
- 4.2 All surfaces to be coated shall be grit blasted to a near-white finish (SSPC SP-10, NACE No. 2 or Sa 2 1/2). *Note: Near-white finish is interpreted to mean that all metal surfaces shall be blast cleaned to remove all dirt, mill scale, rust, corrosion products, oxides, paint and other foreign matter. Very light shadow, very light streaks or slight discolorations shall be acceptable; however, at least 95% of the surface shall have the uniform gray appearance of a white metal blast-cleaned surface as defined by Swedish*

*Pictorial Surface Preparation Standard Sa 2 1/2 or SSPC VIS-1.*

- 4.3 Edges of the existing coating shall be roughened by power brushing or by sweep blasting the coating for a distance of 1" (25 mm) minimum.
- 4.4 All contaminants shall be removed from the steel surface to be coated. Oil and grease should be removed in accordance with SSPC SP-1 using non-oily solvent cleaner (i.e., xylene, MEK, ethanol, etc.).
- 4.5 The Contractor shall check the surface profile depth by using a suitable surface profile gauge (Press-O-Film Gauge or equal).
- 4.6 Metal areas that develop flash rust due to exposure to rain or moisture shall be given a sweep blast to return them to their originally blasted condition.

### 5.0 Application

- 5.1 The surface shall have no condensation, precipitation or any other forms of contamination on the blasted surface prior to coating.
- 5.2 The substrate temperature range for application of Protal™ 7900HT is 40°F (4°C) to 220°F (105°C). The substrate temperature must be a minimum of 5°F (3°C) above the dew point temperature before proceeding with the coating operation.
- 5.3 Protal™ shall be applied to the specified Dry Film Thickness (DFT) up to 40 mils (1016 microns) using a brush, Denso applicator pad or roller. Wet film measurements shall be performed to ensure close adherence to the thickness specification.
- 5.4 Mixing: Make sure the part A (Resin) and Part B (Hardener) components match in both material and size as specified on the containers. Mix the B component first, independent of the resin. Pour the contents into the part A (Resin) component. Mix at a slow speed so as not to create a vortex that could introduce air into the product until a uniform colour is achieved making sure to scrape the bottom and sides of the container (approximately 2 minutes). No streaks shall be visible.

- 5.5 APPLICATION SHALL TAKE PLACE IMMEDIATELY AFTER MIXING. Apply the product onto the surface and spread down and around the surface in bands beginning from the leading edge of the material to as far under the pipe as can be reached. Overlap the bands and onto the existing coating a minimum of 1" (25 mm). Applicators shall use a brush to smooth out any obvious sags or rough edges, valleys, or drips. Special attention shall be given to weld buttons and bottom surfaces.
- 5.6 The thickness of Protal™ shall be checked periodically by wet film gauge to achieve the minimum and maximum wet film thickness specified. After the Protal™ has cured, the owner's representative and/or contractor's inspector should measure the film thickness by magnetic gauge and notify the applicator of their acceptance. Notification to the applicator of any inadequately coated sections must be made immediately.
- 5.7 Over-coating, when necessary, shall take place within 4 hours at 80°F (27°C). If recoat window has lapsed, The surface shall be roughed prior to application of the topcoat using 80 grit sand paper or by sweep blasting.

## 6.0 Inspection/Testing for Backfill

- 6.1 The finished coating shall smooth and free of protuberances or holidays. All surfaces shall have the required minimum/maximum DFT. Inspection of brush application is best performed immediately after application.
- 6.2 Backfill time shall be determined by the "thumb nail test". The thumb nail test is defined by when one can no longer make a permanent indentation in the coating with his or her thumb nail. *Note: A full and/or chemical cure may not be achieved by backfill time. Therefore, in wet soils or water the coating will need a full chemical cure. (refer to Section 6.3 for acceptable field test for chemical cure)*
- 6.3 An acceptable field test to check to see if the coating has a full chemical cure, a solvent such as Xylene, MEK or Toluene can be rubbed on to the coating. If the gloss/sheen is removed the coating is not fully cured.
- 6.4 Spark testing shall be performed to ensure proper film thickness and for holiday inspection. The voltage used for testing weld joints and field applications shall be equal to that used for testing the mainline coating in the field or 125 volts/mil (4,920 V/mm).
- 6.5 Denso and/or the owner's representative, immediately upon completion of the work, shall make final inspection of the completed application. Notification of all defects must be made within a reasonable time frame from completion of the work to allow for all repairs within the allowed time frame for the project.

## 7.0 Repairs

- 7.1 Repair areas may be accomplished by using Protal™ 7900HT or approved products. Repair areas shall be roughened a minimum of 1" (25 mm) around defect using a carborundum cloth or 80 grit sandpaper and wiped clean with a cloth or brush prior to patching. Please note that areas larger than 1.0 sq. ft. (100 sq. cm.) may require grit blasting prior to repairing.

## 8.0 Safety Precautions

- 8.1 Follow the guidelines detailed in the Safety Data Sheets (SDS).
- 8.2 Keep containers closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with applicable regulations.
- 8.3 Always refer to project specifications as they may supercede Denso specifications.



**DENSO (AUSTRALIA) PTY LTD**  
77 - 95 National Boulevard  
Campbellfield, VIC 3061  
Tel: +61 3 9356 7600  
Fax: +61 3 9356 7699

[www.densoaustralia.com.au](http://www.densoaustralia.com.au)

**A Member of the Winn & Coales International**